



Fig. 1

规格Type	尺寸Dimensions(mm)							有效参数Effective Parameters				BP44	BP95	
	A	B	C	D	E	F	I	C1(mm ⁻¹)	Ae(mm ²)	Le(mm)	Ve(mm ³)	电感系数AL(nH/N ²)		重量(克/付)Wt(g/set)
EI20/16	20.00±0.4	13.55±0.2	5.00±0.25	4.55±0.0	13.9 min	11.15±0.2	2.3±0.2		24.50	39.60	970.20	1350±25%	1750±25%	6.20
EI22/18	22.00±0.5	14.60±0.2	5.70±0.25	5.70±0.25	15.8 min	11.00±0.2	3.6±0.2	1.70	34.60	42.70	1477.42	1800±25%	2200±25%	9.50
EI28/21	28.00±0.6	17.15±0.2	10.75±0.25	7.25±0.25	18.6 min	12.65±0.3	3.5±0.2	0.57	85.00	48.70	4150.00	3600±25%	4500±25%	26.20
EI28.5/21	28.60±0.5	17.00±0.2	10.70±0.25	7.25±0.25	20.0 min	12.70±0.25	3.5±0.2		81.20	50.80	4124.96	3600±25%	4500±25%	23.90
EI33/29	33.00±0.6	24.00±0.3	12.70±0.30	9.50±0.30	23.4 min	19.30±0.3	4.7±0.3	0.57	118.20	67.60	7990.32	3800±25%	4600±25%	42.80
EI40/34	40.00±0.8	27.00±0.3	11.65±0.25	11.45±0.25	27.3 min	21.20±0.3	6.8±0.3	0.55	141.20	77.50	10953.0	4500±25%	5500±25%	62.80

注: AL值测试条件:1KHz、 0.3V、 100Ts 。(Remark:Testing conditon for AL:1KHz、 0.3V、 100Ts.)

以上为本公司标准规格, 可根据客户特殊要求进行设计。(The above is the usually type, we can redesign according to costomer's requ