

ATQ型功率铁氧体产品系列

		尺寸Dimensions(mm)										有效参数Effective parameter				电感系数AL(nH/N ²)		重量(克/付)
规格Type	图形Fig	A	B	C/C1	C2	D1	D2	E1	E2	E3	F	Ae(mm ²)	Acw(mm ²)	Le(mm)	Ve(mm ³)	BP44	BP95	Wt(g/set)
ATQ17.2/12.4	1	17.20±0.35	6.2±0.15	14.4±0.35	10.15±0.3	9.7±0.25	6.10±0.2	14.2±0.35	12.7±0.35	-	4.10±0.15	50.2	33.21	31.0	1556.2	3000±25%	3800±25%	9.80
ATQ27/10	1	27.00±0.5	5.1±0.15	22.5±0.5	17.3±0.4	14.2±0.25	11.2±0.25	23.2±0.50	19.0±0.50	15.0±0.5	2.20±0.15	132.0	26.4	34.6	4567.20	6800±25%	9000±25%	23.70
ATQ27/18.1L-1	1	27.00±0.4	9.05±0.10	20.0±0.3	15.25±0.25	14.2±0.25	11.2±0.25	22.0±0.40	17.04±0.4	16.2±0.4	5.80±0.15	128.0	62.6	45.8	5862.00	6100±25%	8000±25%	43.20
ATQ28/18.4F-1	2	28.00±0.4	9.20±0.15	24.3±0.4	18.35±0.3	15.3±0.25	13.0±0.25	24.3±0.40	17.90±0.4	13.6±0.4	5.80±0.15	155.00	65.54	45.80	7099.00	7700±25%	10000±25%	43.80
ATQ28/14.6	3	28.00±0.5	7.3±0.15	16.0±0.3	18.35±0.3	13.0±0.25	10.5±0.20	23.2±0.45	19.4±0.45	16.6±0.45	3.70±0.15	111.50	46.99	39.80	4436.00	6000±25%	7800±25%	26.90
ATQ22/17.8	4	22.10±0.4	8.9±0.15	14.1±0.4	12.0±0.3	9.0±0.20	8.7±0.2	17.8±0.40	14.9±0.40	-	6.35±0.15	68.1	57.79	44.6	3037.26	3300±25%	4100±25%	18.20
ATQ31/19.6	5	31.00±0.5	9.8±0.20	27.6±0.45	-	17.8±0.3	13.7±0.20	24.0±0.50	18.8±0.45	-	6.30±0.20	209.10	64.89	53.30	11153.00	8500±25%	10500±25%	62.00
ATQ23.7/13	6	23.70±0.4	6.5±0.15	17.8±0.4	14.7±0.3	9.6±0.25	12.2±0.25	21.0±0.40	13.40min	13.40min	3.50±0.15	98.0	30.8	35.4	3469.2	5500±25%	6800±25%	20.50

注: AL值测试条件:1KHz、0.3V、100Ts。(Remark:Testing conditon for AL:1KHz、0.3V、100Ts.)

以上为本公司标准规格,可根据客户特殊要求进行设计。(The above is the usually type, we can redesign according to costomer's requ