

## U型功率铁氧体产品系列

Fig.1		Fig.2		Fig.3		Fig.4		Fig.5		Fig.6		
规格Type	图形Fig	尺寸Dimensions(mm)							抗压强度 (N)	Q值	电感系数AL(nH/N <sup>2</sup> )	重量(克/只)
		A	B	C	D	D1	E	H	Strength (N)	Q	BP40/PC95	Wt(g/set)
U40.5×15×13	1	40.1±0.4	15.0±0.2	13.00±0.20	4.5±0.2	/	/	5.0±0.2	≥160	≥1.10	≥500	18.2
U48.4×13.2×14.8	1	48.4±0.5	14.8±0.2	13.20±0.20	4.5±0.2	/	/	/	≥160	≥1.50	≥600	19.90
U55.5×13.2×16	1	55.5±0.5	16.0±0.3	13.20±0.20	4.5±0.2	/	/	/	≥160	≥1.60	≥690	22.70
U60×13.2×15	2	60±0.5	15.0±0.2	13.20±0.20	4.5±0.2	/	/	4.5±0.2	≥160	≥1.80	≥700	23.00
U60.5×12.5×19.3	2	60.5±0.7	19.3±0.2	12.50±0.20	4.5±0.2	/	/	5.0±0.2	≥200	> 1.20	> 720	25.40
U60.5×13.0×15.4	2	60.5±0.5	15.4±0.15	13.00±0.20	4.5±0.2			5.3±0.1	≥200	> 1.85	> 710	25.50
U63.8×15×16	3	63.6±0.4	16.0±0.2	14.90±0.20	/	/	52.5min	5.3±0.2	≥200	≥2.00	≥790	31.90
U73×13.2×14	2	73±0.7	14.0±0.2	13.20±0.20	4.5±0.1			4.5±0.1	≥160	≥1.50	≥720	25.80
U78.2×13.2×14.8	1	78.2±0.5	14.8±0.2	13.20±0.20	4.5±0.2	/	/	/	≥160	≥1.80	≥800	28.30
U78.2×18.8×12.5	5	78.2±0.7	18.8±0.3	12.50±0.20	4.9±0.2	4.50±0.2	/	6±0.1	≥200	≥1.90	≥860	31.20
U78×9.0×18.0	1	78±0.7	9.00±0.3	18.00±0.30	5±0.2	/	/	4.5±0.2	≥160	≥1.80	≥800	25.80
U78.3×24×14	6	78.3±0.4	24.0±0.3	14.00±0.30	10±0.25	/	67.3±0.4	10±0.25	/	/	/	74.50
U79.1×16.0×4.5	4	79.1±0.6	16.0±0.2	/	5.8±0.2	4.50±0.2	/	4.5±0.2	≥160	≥2.50	≥950	45.00
U92*22*10	1	92±1	22.0±0.3	10.00±0.30	10±0.3	10.0±0.3	/	/	/	/	/	53.90

注: 1. AL值测试条件:1KHz、 0.3V、 100Ts。(Remark:Testing conditon for AL:1KHz、 0.3V、 100Ts.)

2.Q值测试条件:1KHz、 1V、 100Ts。(Q:Testing conditon for AL:1KHz、 1V、 100Ts.)

3.抗压强度测试条件: 测试间距40mm, 测试速度: 30mm/mim.

以上为本公司标准规格, 可根据客户特殊要求进行设计。(The above is the usually type, we can redesign according to costomer's request)